

MATERIAL GROUPS

According to DIN / ISO 513 and VDI 3323

ISO	Material	Condition	Tensile Strength [N/mm ²]	Kc1 ⁽¹⁾ [N/mm ²]	mc ⁽²⁾	Hardness HB	Material No.	
P	Non-alloy steel and cast steel, free cutting steel	< 0.25 %C	Annealed	420	1350	0.21	125	1
		>= 0.25 %C	Annealed	650	1500	0.22	190	2
		< 0.55 %C	Quenched and tempered	850	1675	0.24	250	3
		>= 0.55 %C	Annealed	750	1700	0.24	220	4
	Quenched and tempered		1000	1900	0.24	300	5	
	Low alloy steel and cast steel (less than 5% of alloying elements)	Annealed	600	1775	0.24	200	6	
		Quenched and tempered	930	1675	0.24	275	7	
			1000	1725	0.24	300	8	
	High alloyed steel, cast steel, and tool steel	Annealed	680	2450	0.23	200	10	
		Quenched and tempered	1100	2500	0.23	325	11	
	Stainless steel and cast steel	Ferritic/martensitic	680	1875	0.21	200	12	
		Martensitic	820	1875	0.21	240	13	
	M	Stainless steel	Austenitic, duplex	600	2150	0.20	180	14
K	Grey cast iron (GG)	Ferritic/pearlitic		1150	0.20	180	15	
		Pearlitic		1350	0.28	260	16	
	Nodular cast iron (GGG)	Ferritic		1225	0.25	160	17	
		Pearlitic		1350	0.28	250	18	
	Malleable cast iron	Ferritic		1225	0.25	130	19	
Pearlitic			1420	0.3	230	20		
N	Aluminum-wrought alloy	Not hardenable		700	0.25	60	21	
		Hardenable		800	0.25	100	22	
	Aluminum-cast, alloyed	<=12% Si	Not hardenable		700	0.25	75	23
		Hardenable		700	0.25	90	24	
	Copper alloys	>12% Si	High temperature		750	0.25	130	25
		>1% Pb	Free cutting		700	0.27	110	26
			Brass		700	0.27	90	27
			Electrolytic copper		700	0.27	100	28
	Non metallic	Duroplastics, fiber plastics						29
		Hard rubber						30
S	High temperature alloys	Fe based	Annealed		2600	0.24	200	31
			Hardened		3100	0.24	280	32
		Ni or Co based	Annealed		3300	0.24	250	33
			Hardened		3300	0.24	350	34
			Cast		3300	0.24	320	35
	Titanium alloys	Pure	RM 400	1700	0.23		36	
		Alpha+beta alloys hardened	RM 1050	2110	0.22		37	
H	Hardened steel	Hardened		4600		55 HRC	38	
		Hardened		4700		60 HRC	39	
	Chilled cast iron	Cast		4600		400	40	
	Cast iron	Hardened		4500		55 HRC	41	

Steel Stainless Steel Cast Iron

Nonferrous High Temp. and Titanium Alloys Hardened Steel and Cast Iron

⁽¹⁾ Specific cutting force for 1 mm² chip section. (see page 523).

⁽²⁾ Chip thickness factor. (see page 523).